

PRECISIONHYTEC



Specialists in Rubber & Rubber Products, Gaskets & Washers. Serving Business & Community since 1949.

HYTEC RUBBER 65874 INSERTION RUBBER IS MANUFACTURED TO SURPASS THE FOLLOWING STANDARD MAC-8887

COMPOUND PETROL 23 X 24 HRS	TENSILE STRENGTH RANGE	MAXIMUM ELONGATION	HARDNESS	AGEING 72HRS X 70C	HOT OIL 70 X 24HRS SWELL
65874	7	250%	60/70	0.75%	+25%

A TYPE BATCH RESULT IS AS FOLLOWS

- TENSILE STRENGTH MPA 8.6 – 7.8
- ELONGATION AT TEAR 337 – 380%
- HARDNESS RANGE SHORE A 65 +/- 5
- AGEING [70C X 24HRS] 0.80 – 1.20
- HOT OIL [70 X 24HRS] + 4 - +6 %
- PETROL IMMERSION 23 X 24HRS + 12 – 17.8%

