

PRECISIONHYTEC



Specialists in Rubber & Rubber Products, Gaskets & Washers. Serving Business & Community since 1949.

HYTEC RUBBER 3706 NEOPRENE RUBBER IS MANUFACTURED TO SURPASS THE FOLLOWING STANDARD GB 557-6

COMPOUND PETROL 23 X 24 HRS	TENSILE STRENGTH RANGE	MAXIMUM ELONGATION	HARDNESS	AGEING 72HRS X 70C	HOT OIL 70 X 24HRS SWELL
65874		250%	63/73	0.75%	+18% +25%

A TYPE BATCH RESULT IS AS FOLLOWS

- TENSILE STRENGTH MPA 8.6 – 7.8
- ELONGATION AT TEAR 337 – 380%
- HARDNESS RANGE SHORE A 68 +/- 5
- AGEING [70C X 24HRS] 0.80 – 1.20
- HOT OIL [70 X 24HRS] + 4 - +6 %

PRECISIONHYTEC

