

PRECISIONHYTEC



Specialists in Rubber & Rubber Products, Gaskets & Washers. Serving Business & Community since 1949.

HYTEC RUBBER 3602 WHITE RUBBER IS MANUFACTURED TO SURPASS THE FOLLOWING STANDARD G.B. 557-8

COMPOUND	TENSILE STRENGTH RANGE	MAXIMUM ELONGATION	HARDNESS	AGEING 72HRS X 70C	HOT OIL 70 X 24HRS SWELL
3602	7	250%	60/65	0.75%	+8%

A TYPE BATCH RESULT IS AS FOLLOWS

1. TENSILE STRENGTH MPA 8.4 – 7.6
2. ELONGATION AT TEAR 347 – 387%
3. HARDNESS RANGE SHORE A 60 /65
4. AGEING [70C X 24HRS] 0.89 – 1.16

